GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10028-6 P500QL1 I 1.8875

Standard Specification for Flat Products Made of Steels for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10028-6 P500QL1 I 1.8875 Flat Products Made of Steels for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.180 max.
Silicon	Si %	0.600 max.
Manganese	Mn %	1.700 max.
Phosphorus	P %	0.020 max.
Sulphur	S %	0.008 max.
Nitrogen	N %	0.015 max.
Boron	B %	0.005 max.
Chromium	Cr %	1.000 max.
Molybdenum	Mo %	0.700 max.
Copper	Cu %	0.300 max.
Niobium	Nb %	0.050 max.
Nickel	Ni %	1.500 max.
Titanium	Ti %	0.050 max.
Vanadium	V %	0.080 max.
Zirconium	Zr %	0.150 max.

Chemical Composition		
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
Heat Treatment		
As-Raw or Quenching & Tempering		
Mechanical Properties		
Tensile Strength in Mpa	590 - 770	
Yield Strength in Mpa	500 min.	
Elongation in %	17 min.	
Reduction of Area in %	-	
Hardness in HB	-	
Impact in Joule	60 @ RT	

www.gravitycastindia.com

Cross Reference Table

Material	Standard	Country	Grade Belong to the Industry
EN 10028-6 P 500 QL1	AFNOR NF	France	Steel
EN 10028-6 P500QL1	DIN	Germany	Steel
EN 10028-6 1.8875	DIN	Germany	Steel
EN 10028-6 P500QH	DIN	Germany	Steel
EN 10028-6 1.8874	DIN	Germany	Steel
10028-6 1.8874	EN	European Union	Steel
10028-6 1.8865	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.