GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10088-1 1.4037 (X65Cr13)

Standard Specification for Stainless Steel

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10088-1 1.4037 (X65Cr13) Stainless Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.580 - 0.700
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	12.500 - 14.500
Nitrogen	N %	0.200 max.
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Quenching + Tempering

Mechanical Properties	
Tensile Strength in Mpa	-
Proof Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HRB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
X 65 Cr 13	DIN	Germany	Steel
SEW 400 1.4037	DIN	Germany	Steel
3583 40 Cr 130	STAS	Romania	Steel
EN 10088-1 X39Cr13	AFNOR NF	France	Steel
EN 10088-2 X39Cr13	AFNOR NF	France	Steel
EN 10088-3 X39Cr13	AFNOR NF	France	Steel
10088-3 X 39 Cr 13	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.