GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10088-1 1.4606 (X5NiCrTiMoVB25-15-2)

Standard Specification for Stainless Steel

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10088-1 1.4606 (X5NiCrTiMoVB25-15-2) Stainless Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 - 2.000
Phosphorus	P %	0.025 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	13.000 - 16.000
Molybdenum	Mo %	1.000 - 1.500
Nickel	Ni %	24.000 - 27.000
Boron	B %	0.001 - 0.010
Aluminium	Al %	0.350 max.
Titanium	Ti %	1.900 - 2.300
Vanadium	V %	0.100 - 0.500
Iron	Fe %	Balance
-	-	-
-	-	-

Heat Treatment
As-Raw or precipitation Hardening

Mechanical Properties	
Tensile Strength in Mpa	-
Proof Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HRB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S66286	UNS	USA	Steel
1.4954	DIN	Germany	Steel
1.4944	DIN	Germany	Steel
142570 2570	SS	Sweden	Steel
1506 286 S 31	B.S.	United Kingdom	Steel and Bars
10269 X 6 NiCrTiMoVB 25-15-2	EN	European Union	Steel
10269 1.4980	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.