GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10088-1 1.4948 (X6CrNi18-10)

Standard Specification for Stainless Steel

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10088-1 1.4948 (X6CrNi18-10) Stainless Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.040 - 0.080
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	17.000 - 19.000
Nickel	Ni %	8.000 - 11.000
Nitrogen	N %	0.100 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	-
Proof Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HRB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
36087-4 F.3504	UNE	Spain	Steel
36016-2 F.3504	UNE	Spain	Steel
2604-1 F47	ISO	International	Steel
9327-5 F47	ISO	International	Steel and Bars
10222-5 1.4948	EN	European Union	Steel and Forging
10269 1.4948	EN	European Union	Steel
EN 10028-7 1.4948	DIN	Germany	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.