GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10088-3 1.4520 (X2CrTi17)

Standard Specification for Semi-Finished Products, Bars, Rods, Wire, Sections and Bright Products of Corrosion Resistant Steels for General Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10088-3 1.4520 (X2CrTi17) Semi-Finished Products, Bars, Rods, Wire, Sections and Bright Products of Corrosion Resistant Steels for General Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars, Rods and Wire

Chemical Composition		
Carbon	C %	0.025 max.
Silicon	Si %	0.500 max.
Manganese	Mn %	0.500 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	16.000 - 18.000
Nitrogen	N %	0.015 max.
Titanium	Ti %	0.158 - 0.800
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Quenching + Tempering

Mechanical Properties	
Tensile Strength in Mpa	420 - 620
Proof Strength in Mpa	200 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in HBW	200 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN 10088-2 X 2 CrTi 17	UNI	Italy	Steel and Casting
EN 10088-1 X2CrTi17	AFNOR NF	France	Steel
EN 10088-2 X2CrTi17	DIN	Germany	Steel
EN 10088-1 X2CrTi17	DIN	Germany	Steel
EN 10028-7 X2CrTi17	DIN	Germany	Steel
10028-7 X 2 CrTi 17	EN	European Union	Steel
10088-1 X 2 CrTi 17	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.