GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10088-3 1.4652 (X1CrNiMoCuN24-22-8)

Standard Specification for Semi-Finished Products, Bars, Rods, Wire, Sections and Bright Products of Corrosion Resistant Steels for General Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10088-3 1.4652 (X1CrNiMoCuN24-22-8) Semi-Finished Products, Bars, Rods, Wire, Sections and Bright Products of Corrosion Resistant Steels for General Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars, Rods and Wire

Chemical Composition		
Carbon	C %	0.020 max.
Silicon	Si %	0.500 max.
Manganese	Mn %	2.000 - 4.000
Phosphorus	P %	0.030 max.
Sulphur	S %	0.005 max.
Chromium	Cr %	23.000 - 25.000
Nickel	Ni %	21.000 - 23.000
Molybdenum	Mo %	7.000 - 8.000
Nitrogen	N %	0.450 - 0.550
Copper	Cu %	0.300 - 0.600
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	750 - 1000
Proof Strength in Mpa	470 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in HBW	310 max.
Impact in Joule	100 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S32654	UNS	USA	Steel
A 167 S32654	ASTM	USA	Plate, Sheet and Strip
A 249 S32654	ASTM	USA	Steel and Tubing
A 269 S32654	ASTM	USA	Steel and Tubing
SA-240 UNS S32654	ASME	USA	Plate, Sheet and Strip
SA-249 UNS S32654	ASME	USA	Steel and Tubing
SA-312 UNS S32654	ASME	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.