GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10088-4 1.4477 (X2CrNiMoN29-7-2)

Standard Specification for Sheet/Plate and Strip of Corrosion Resisting Steels for Construction Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10088-4 1.4477 (X2CrNiMoN29-7-2) Sheet/Plate and Strip of Corrosion Resisting Steels for Construction Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	0.500 max.
Manganese	Mn %	0.800 - 1.500
Phosphorus	P %	0.030 max.
Sulphur	S %	0.015 max.
Nitrogen	N %	0.300 - 0.400
Chromium	Cr %	28.000 - 30.000
Copper	Cu %	0.800 max.
Molybdenum	Mo %	1.500 - 2.600
Nickel	Ni %	5.800 - 7.500
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Quenching + Tempering

Mechanical Properties	
Tensile Strength in Mpa	800 - 1050
Proof Strength in Mpa	650 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in HRB	-
Impact in Joule	100 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S32906	UNS	USA	Steel
A 240 S32906	ASTM	USA	Plate, Sheet and Strip
A 789 S32906	ASTM	USA	Steel and Tubing
A 959 S32906	ASTM	USA	Steel
10088-1 1.4477	EN	European Union	Steel
10088-1 X2CrNiMoN29-7-2	EN	European Union	Steel
10088-2 1.4477	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.