GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

# Material - BS EN 10088-4 1.4512 (X2CrTi12)

## Standard Specification for Sheet/Plate and Strip of Corrosion Resisting Steels for Construction Purposes

**Group - Ferrous Stainless Steel Alloys**

**Sub Group - BS EN 10088-4 1.4512 (X2CrTi12) Sheet/Plate and Strip of Corrosion Resisting Steels for Construction Purposes**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Plate, Sheet and Strip**

| Chemical Composition | | |
|---|---|---|
| Carbon | C % | 0.030 max. |
| Silicon | Si % | 1.000 max. |
| Manganese | Mn % | 1.000 max. |
| Phosphorus | P % | 0.040 max. |
| Sulphur | S % | 0.015 max. |
| Chromium | Cr % | 10.500 - 12.500 |
| Titanium | Ti % | 0.012 - 0.650 |
| Iron | Fe % | Balance |
| - | - | - |
| - | - | - |
| - | - | - |
| - | - | - |
| - | - | - |
| - | - | - |

| Heat Treatment |
|---|
| As-Raw or Annealing or Quenching + Tempering |

| Mechanical Properties | |
|---|---|
| Tensile Strength in Mpa | 380 - 560 |
| Proof Strength in Mpa | 220 min. |
| Elongation in % | 25 min. |
| Reduction of Area in % | - |
| Hardness in HRB | - |
| Impact in Joule | - |

www.gravitycastindia.com

| Cross Reference Table | | | |
|---|---|---|---|
| **Material** | **Standard** | **Country** | **Grade Belong to the Industry** |
| 17456 1.4512 | DIN | Germany | Steel and Tubing |
| 5512-3 1.4512 | DIN | Germany | Steel |
| SEW 400 1.4512 | DIN | Germany | Steel and Forging |
| EN 10088-3 1.4512 | DIN | Germany | Steel |
| EN 10088-2 1.4512 | DIN | Germany | Steel |
| EN 10088-1 1.4512 | DIN | Germany | Steel |
| 10088-1 1.4512 | EN | European Union | Steel |

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.