GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10088-4 1.4565 (X2CrNiMnMoN25-18-6-5)

Standard Specification for Sheet/Plate and Strip of Corrosion Resisting Steels for Construction Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10088-4 1.4565 (X2CrNiMnMoN25-18-6-5) Sheet/Plate and Strip of Corrosion Resisting Steels for Construction Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	5.000 - 7.000
Phosphorus	P %	0.030 max.
Sulphur	S %	0.015 max.
Nitrogen	N %	0.300 - 0.600
Chromium	Cr %	24.000 - 26.000
Molybdenum	Mo %	4.000 - 5.000
Niobium	Nb %	0.150 max.
Nickel	Ni %	16.000 - 19.000.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	800 - 950
Proof Strength in Mpa	460 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in HRB	-
Impact in Joule	120 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
SEW 400 1.4565	DIN	Germany	Steel and Forging
10088-3 1.4565	EN	European Union	Steel
10088-3 X2CrNiMnMoN25-18-6-5	EN	European Union	Steel
10088-2 1.4565	EN	European Union	Steel
10088-2 X2CrNiMnMoN25–18–6-5	EN	European Union	Steel
10088-1 1.4565	EN	European Union	Steel
10088-1 X2CrNiMnMoN25-18-6-5	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.