GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10088-5 1.4311 (X2CrNiN18-10)

Standard Specification for Bars, Rods, Wire, Sections and Bright Products of Corrosion Resisting Steels for Construction Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10088-5 1.4311 (X2CrNiN18-10) Bars, Rods, Wire, Sections and Bright Products of Corrosion Resisting Steels for Construction Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars, Rods and Wire

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Nitrogen	N %	0.120 - 0.220
Chromium	Cr %	17.500 - 19.500
Nickel	Ni %	8.500 - 11.500
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	550 - 760
Proof Strength in Mpa	305 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in HBW	230 max.
Impact in Joule	100 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
M 3121 X 2 CrNiN 18 10 KKW	ONORM	Austria	Steel
9327-5 X 2 CrNiN 18 10	ISO	International	Steel and Bars
36016-1 X 2 CrNiN 18 10	UNE	Spain	Steel
EN 10088-2 X 2 CrNiN 18-10	UNI	Italy	Steel and Casting
EN 10088-1 X2CrNiN18-10	AFNOR NF	France	Steel
EN 10088-2 X 2 CrNiN 18 10	DIN	Germany	Steel
10088-3 X 2 CrNiN 18 10	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.