



Material - BS EN 10213 G17MoCrV5-10

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10213 G17MoCrV5-10 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Tubes and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.200		
Silicon	Si %	0.600 max.	Normalizing or Quenching or Solution Annealing	
Manganese	Mn %	0.500 - 0.900		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	1.200 - 1.500		
Molybdenum	Mo %	0.900 - 1.100		
Nickel	Ni %	0.400 max.		
Copper	Cu %	0.300 max.	Mechanical Properties	
Vanadium	V %	0.200 - 0.300	Tensile Strength in Mpa	440 min.
Tin	Sn %	0.025 max.	Yield Strength in Mpa	385 min.
Iron	Fe %	Balance	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	27 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
-	-	-	-	
-	-	·	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.