



Material - BS EN 10213 G20Mn5

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10213 G20Mn5 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Tubes and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.170 - 0.230	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 - 1.600		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.300 max.		
Molybdenum	Mo %	0.120 max.		
Nickel	Ni %	0.800 max.		_
Copper	Cu %	0.300 max.	Mechanical Properties	
Vanadium	V %	0.030 max.	Tensile Strength in Mpa	300 min.
Iron	Fe %	Balance	Yield Strength in Mpa	270 min.
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1.6220	ISO	International	Casting	
G20Mn5	ISO	International	Casting	
GS-20 Mn 5	DIN	Germany	Casting	
SCC 3	JIS	Japan	Casting	
SCPH 11-CF	JIS	Japan	Casting	
SCW 520-CF	JIS	Japan	Casting	
SCW 550	JIS	Japan	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.