



Material - BS EN 10213 GX15CrMo5

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10213 GX15CrMo5 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Tubes and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 - 0.190	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.800 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	4.000 - 6.000		
Molybdenum	Mo %	0.450 - 0.650		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 420 min. Yield Strength in Mpa 390 min. Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule 27 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
GX15CrMo5	ISO	International	Casting
1.7365	ISO	International	Casting
SCPH 61	JIS	Japan	Casting
A 217 Grade C5	ASTM	USA	Casting
A 217 J42045	ASTM	USA	Casting
1.7365	BS	British	Casting
GX 15 CrMo 5	SS	Sweden	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.