GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10213 GX2NiCrMo28-20-2 I 1.4458

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10213 GX2NiCrMo28-20-2 I 1.4458 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.025 max.
Chromium	Cr %	19.000 - 22.000
Molybdenum	Mo %	2.000 - 2.500
Nickel	Ni %	26.000 - 30.000
Copper	Cu %	2.000 max.
Nitrogen	N %	0.200 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	430 - 630
Proof Strength in Mpa	190 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	60 @ -196˚C

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN 10213-4 1.4458	DIN	Germany	Casting
17445 1.4458	DIN	Germany	Casting
EN 10213-4 G X 2 NiCrMo 28-20-2	UNI	Italy	Casting
EN 10213-4 GX2NiCrMo 28-20-2	AFNOR NF	France	Casting
10283 GX 2 NiCrMo 28 20 2	EN	European Union	Casting
10283 1.4458	EN	European Union	Casting
10213-4 1.4458	EN	European Union	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.