



## Material - BS EN 10213 GX8CrNi12

## **Standard Specification for Steel Castings for Pressure Purposes**

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - BS EN 10213 GX8CrNi12 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Tubes and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.		
Silicon	Si %	0.400 max.	Normalizing or Quenching or Solution Annealing	
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.030 max.		or Solution Annealing
Sulphur	S %	0.020 max.		
Chromium	Cr %	11.500 - 12.500		
Molybdenum	Mo %	0.500 max.		
Nickel	Ni %	0.800 - 1.500		
Copper	Cu %	0.300 max.	Mechanical Properties	
Vanadium	V %	0.800 max.	Tensile Strength in Mpa	355 min.
Iron	Fe %	Balance	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-		Impac <mark>t in Joule</mark>	45 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
GX8CrNi12-1	ISO	International	Casting	
1.4107	ISO	International	Casting	
SCS 1	JIS	Japan	Casting	
GX 8 CrNi 12	ONORM	Australia	Casting	
1.4107	ONORM	Australia	Casting	
GX 8 CrNi 12	NBN	Belgium	Casting	
1.4107	NBN	Belgium	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.