GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10216-3 P620Q I 1.8876

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10216-3 P620Q I 1.8876 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tubing

Chemical Composition		
Carbon	C %	0.200 max.
Silicon	Si %	0.600 max.
Manganese	Mn %	1.000 - 1.700
Phosphorus	P %	0.025 max.
Sulphur	S %	0.020 max.
Chromium	Cr %	0.300 max.
Molybdenum	Mo %	0.100 max.
Nickel	Ni %	0.800 max.
Aluminium	Al %	0.020 min.
Copper	Cu %	0.300 max.
Nitrogen	N %	0.020 max.
Niobium	Nb %	0.050 max.
Titanium	Ti %	0.040 max.
Vanadium	V %	0.200 max.
Nb + Ti + V	Nb% + Ti% + V%	0.220 max.

Chemical Composition		
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
Heat Treatment		
As-Raw or Quenching & Tempering		
Mechanical Properties		
Tensile Strength in Mpa	740 - 930	
Yield Strength in Mpa	620 min.	
Elongation in %	16 min.	
Reduction of Area in %	-	
Hardness in HB	-	
Impact in Joule	55 @ RT	

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN 10208-2 1.0582	DIN	Germany	Steel and Pipe
17179 1.8902	DIN	Germany	Steel and Tubing
17179 1.8905	DIN	Germany	Steel and Tubing
A 36-207 A 590 FP	AFNOR NF	France	Steel
EN 10028-3 P 460 NL 1	B.S.	United Kingdom	Steel
10028-3 1.8915	EN	European Union	Steel
10028-3 1.8905	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.