GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10216-3 P690Q I 1.8879

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10216-3 P690Q I 1.8879 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tubing

Chemical Composition		
Carbon	C %	0.200 max.
Silicon	Si %	0.800 max.
Manganese	Mn %	1.200 - 1.700
Phosphorus	P %	0.025 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	1.500 max.
Molybdenum	Mo %	0.700 max.
Nickel	Ni %	2.500 max.
Aluminium	Al %	0.020 min.
Copper	Cu %	0.300 max.
Nitrogen	N %	0.015 max.
Niobium	Nb %	0.060 max.
Titanium	Ti %	0.050 max.
Vanadium	V %	0.120 max.
Iron	Fe %	Balance

Heat Treatment
As-Raw or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	770 - 960
Yield Strength in Mpa	690 min.
Elongation in %	16 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	55 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN 10028-6 P690QL2	DIN	Germany	Steel
EN 10028-6 1.8888	DIN	Germany	Steel
EN 10028-6 P 690 QL2	AFNOR NF	France	Steel
10028-6 P 690 QL 2	EN	European Union	Steel
10028-6 1.8888	EN	European Union	Steel
10216-3 1.8880	EN	European Union	Steel and Tubing
10216-3 1.8881	EN	European Union	Steel and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.