GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10250-2 S325G I 1.0570

Standard Specification for Open Die Steel Forgings for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10250-2 S325G I 1.0570 Open Die Steel Forgings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition		
Carbon	C %	0.220 max.
Silicon	Si %	0.550 max.
Manganese	Mn %	1.600 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.035 max.
Chromium	Cr %	0.300 max.
Molybdenum	Mo %	0.080 max.
Nickel	Ni %	0.300 max.
Cr + Mo + Ni	Cr% + Mo% + Ni%	0.480 max.
Aluminium	Al %	0.020 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Normalizing or Normalizing & Tempering or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	490 min.
Yield Strength in Mpa	315 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in HRB	-
Impact in Joule	35 @ -20˚C

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN 10208-2 1.0429	DIN	Germany	Steel and Pipe
10208-2 1.0429	EN	European Union	Steel
10222-2 1.0426	EN	European Union	Steel
1502 211	B.S.	United Kingdom	Steel
1502 221	B.S.	United Kingdom	Steel
6280 52 C	MSZ	Hungary	Steel
EN 10028-2 P 295 GH	UNI	Italy	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.