GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10263-3 C20E2C I 1.1152

Standard Specification for Steel Rod, Bars and Wire for Cold Heading and Cold Extrusion

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10263-3 C20E2C I 1.1152 Steel Rod, Bars and Wire for Cold Heading and Cold Extrusion

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Rod, Bars and Wire

Chemical Composition		
Carbon	C %	0.180 - 0.220
Silicon	Si %	0.300 max.
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.025 max.
Sulphur	S %	0.025 max.
Copper	Cu %	0.250 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	640 max.
Proof Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	56 min.
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
9609 08 Ju	BDS	Bulgaria	Steel and Strip
14351 08 Ju	BDS	Bulgaria	Steel and Sheet
2393-2 1.0034	DIN	Germany	Steel and Tubing
2393-2 RSt 34-2 / S205G2T	DIN	Germany	Steel and Tubing
2394-2 1.0034	DIN	Germany	Steel and Tubing
2394-2 RSt 34-2 / S205G2T	DIN	Germany	Steel and Tubing
2391-2 1.0211	DIN	Germany	Steel and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.