GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10263-4 34CrNiMo6 I 1.6582

Standard Specification for Steel Rod, Bars and Wire for Cold Heading and Cold Extrusion

Group - Ferrous Mild Steel Alloys
Sub Group - BS EN 10263-4 34CrNiMo6 I 1.6582 Steel Rod, Bars and Wire for Cold Heading and Cold Extrusion
Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Rod, Bars and Wire

Chemical Composition		
Carbon	C %	0.300 - 0.380
Silicon	Si %	0.300 max.
Manganese	Mn %	0.500 - 0.800
Phosphorus	P %	0.025 max.
Sulphur	S %	0.025 max.
Chromium	Cr %	1.300 - 1.700
Molybdenum	Mo %	0.150 - 0.300
Nickel	Ni %	1.300 - 1.700
Copper	Cu %	0.250 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Quenching + Tempering

Mechanical Properties	
Tensile Strength in Mpa	750 max.
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	58 min.
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN 10083-1 1.6582	DIN	Germany	Steel
SEW 550 1.6582	DIN	Germany	Steel
A 519 4337	ASTM	USA	Steel and Tubing
970-3 817 M 40	B.S.	United Kingdom	Steel
41 6343 16343	CSN	Czech Republic	Steel
4543 38Ch2N2MA	GOST	Russia	Steel
10250-3 1.6582	EN	European Union	Steel and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.