GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10263-4 C35RC I 1.1060

Standard Specification for Steel Rod, Bars and Wire for Cold Heading and Cold Extrusion

Group - Ferrous Mild Steel Alloys
Sub Group - BS EN 10263-4 C35RC I 1.1060 Steel Rod, Bars and Wire for Cold Heading and Cold Extrusion
Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Rod, Bars and Wire

Chemical Composition		
Carbon	C %	0.320 - 0.390
Silicon	Si %	0.300 max.
Manganese	Mn %	0.500 - 0.800
Phosphorus	P %	0.025 max.
Sulphur	S %	0.020 - 0.035
Copper	Cu %	0.250 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Quenching + Tempering

Mechanical Properties	
Tensile Strength in Mpa	670 max.
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
17140-1 1.0516	DIN	Germany	Steel and Wire Rods
17140 1.0516	DIN	Germany	Steel and Wire Rods
1654-4 1.1172	DIN	Germany	Steel
17240 1.1172	DIN	Germany	Steel
G 3506 SWRH 37	JIS	Japan	Steel and Wire Rods
10263-4 C35RC	EN	European Union	Rod, Bars and Wire
10263-4 1.1172	EN	European Union	Rod, Bars and Wire

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.