GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10267 1.1301 (19MnVS6)

Standard Specification for Ferritic-Pearlitic Steels for Precipitation Hardening from Hot-Working Temperatures

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10267 1.1301 (19MnVS6) Ferritic-Pearlitic Steels for Precipitation Hardening from Hot-Working Temperatures

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.150 - 0.220
Silicon	Si %	0.150 - 0.800
Manganese	Mn %	1.200 - 1.600
Phosphorus	P %	0.025 max.
Sulphur	S %	0.020 - 0.060
Nitrogen	N %	0.010 - 0.020
Chromium	Cr %	0.300 max.
Molybdenum	Mo %	0.080 max.
Vanadium	V %	0.080 - 0.200
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or precipitation Hardening

Mechanical Properties	
Tensile Strength in Mpa	600 - 750
Proof Strength in Mpa	390 min.
Elongation in %	16 min.
Reduction of Area in %	32 min.
Hardness in HRB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
10267 19 MnVS 6 + P	EN	European Union	Steel
10267 1.1301 + P	EN	European Union	Steel
10267 1.1302 + P	EN	European Union	Steel
EN 10267 19 MnVS6	AFNOR NF	France	Steel
A 33-111 D 2	AFNOR NF	France	Steel
EN 10267 38 MnVS 6	AFNOR NF	France	Steel
A 33-111 D 4	AFNOR NF	France	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.