GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10272 X2CrNiMnMoCuN24-4-3-2 I 1.4662

Standard Specification for Stainless Steel Bars for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS EN 10272 X2CrNiMnMoCuN24-4-3-2 I 1.4662 Stainless Steel Bars for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	0.700 max.
Manganese	Mn %	2.500 - 4.000
Phosphorus	P %	0.035 max.
Sulphur	S %	0.005 max.
Nitrogen	N %	0.200 - 0.300
Chromium	Cr %	23.000 - 25.000
Copper	Cu %	0.100 - 0.800
Molybdenum	Mo %	1.000 - 2.000
Nickel	Ni %	3.000 - 4.500
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	650 - 900
Proof Strength in Mpa	450 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in HBW	290 max.
Impact in Joule	60 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
9327-5 X 2 CrNiN 234	ISO	International	Bars and Forging
EN 10088-1 X2CrNiN23-4	AFNOR NF	France	Steel
EN 10088-3 X2CrNiN23-4	AFNOR NF	France	Steel
EN 10088-2 X2CrNiN23-4	AFNOR NF	France	Steel
EN 10088-3 X2CrNiN23-4	DIN	Germany	Steel
EN 10088-2 X 2 CrNiN 23-4	UNI	Italy	Steel and Casting
10272 X 2 CrNiN 23 4	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.