GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS EN 10293 1.0558 (GE300)

Standard Specification for Steel Castings for general engineering uses

Group - Ferrous Mild Steel Alloys

Sub Group - BS EN 10293 1.0558 (GE300) Steel Castings for general engineering uses

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Phosphorus	P %	0.035 max.
Sulphur	S %	0.030 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing or Normalizing & Tempering or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	600 - 750
Yield Strength in Mpa	300 min.
Elongation in %	15 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	27 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
A 372 Grade C	ASTM	USA	Steel and Forging
A 302 Grade B	ASTM	USA	Steel and Plate
A 302 Grade C	ASTM	USA	Steel and Plate
A 202 Grade B	ASTM	USA	Steel and Plate
A 302 Grade D	ASTM	USA	Steel and Plate
A 372 Grade E Class 55	ASTM	USA	Steel and Forging
A 487 Grade 1	ASTM	USA	Steel and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.