GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS ISO 16143-1 X2CrNiMoCuWN25-7-4 (4501-327-60-I)

Standard Specification for Stainless Steels for General Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS ISO 16143-1 X2CrNiMoCuWN25-7-4 (4501-327-60-I) Stainless Steels for General Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	24.000 - 26.000
Molybdenum	Mo %	3.000 - 4.000
Nickel	Ni %	6.000 - 8.000
Nitrogen	N %	0.200 - 0.300
Copper	Cu %	0.500 - 1.000
Tungsten	W %	0.500 - 1.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	730 min.
Proof Strength in Mpa	530 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in HBW	-
Impact in Joule	100 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S32760	UNS	USA	Steel
A 240 S32760	ASTM	USA	Plate, Sheet and Strip
A 276 S32760	ASTM	USA	Steel, Bar and Shapes
A 789 S32760	ASTM	USA	Steel and Tubing
SA-240 UNS S32760	ASME	USA	Steel
SA-276 S32760	ASME	USA	Steel, Bar and Shapes
SA-789 UNS S32760	ASME	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.