GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS ISO 16143-1 X2NiCrMoN25-21-7 (4478-083-67-U)

Standard Specification for Stainless Steels for General Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - BS ISO 16143-1 X2NiCrMoN25-21-7 (4478-083-67-U) Stainless Steels for General Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	20.000 - 22.000
Molybdenum	Mo %	6.000 - 7.000
Nickel	Ni %	23.500 - 25.500
Nitrogen	N %	0.180 - 0.250
Copper	Cu %	0.750 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	530 - 730
Proof Strength in Mpa	270 min.
Elongation in %	35 min.
Reduction of Area in %	-
Hardness in HBW	-
Impact in Joule	100 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J94651	UNS	USA	Steel
A 988 N08367	ASTM	USA	Steel
A 959 N08367	ASTM	USA	Steel
A 688 N08367	ASTM	USA	Steel and Tubing
SA-688 UNS N08367	ASME	USA	Steel and Tubing
SA-409 UNS N08367	ASME	USA	Steel and Pipe
SA-358 UNS N08367	ASME	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.