GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS ISO 16143-2 X2CrMnNiN21-5-1g (4162-321-01-Eg)

Standard Specification for Corrosion-Resistant Semi-Finished Products, Bars, Rods and Sections

Group - Ferrous Stainless Steel Alloys

Sub Group - BS ISO 16143-2 X2CrMnNiN21-5-1g (4162-321-01-Eg) Corrosion-Resistant Semi-Finished Products, Bars, Rods and Sections

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars and Rods

Chemical Composition		
Carbon	C %	0.040 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	4.000 - 6.000
Phosphorus	P %	0.040 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	21.000 - 22.000
Molybdenum	Mo %	0.100 - 0.800
Nickel	Ni %	1.350 - 1.900
Nitrogen	N %	0.200 - 0.250
Copper	Cu %	0.100 - 0.800
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	650 min.
Proof Strength in Mpa	400 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in HB	290 max.
Impact in Joule	60 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
A 240 S32101	ASTM	USA	Plate, Sheet and Strip
A 276 S32101	ASTM	USA	Steel, Bar and Shapes
10088-1 1.4162	EN	European Union	Steel
10088-1 X2CrMnNiN21-5-1	EN	European Union	Steel
10088-2 1.4162	EN	European Union	Steel
10088-2 X2CrMnNiN21–5-1	EN	European Union	Steel
10088-3 1.4162	EN	European Union	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.