GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - BS ISO 16143-2 X2CrNiMoCuN25-6-3 (4507-325-20-I)

Standard Specification for Corrosion-Resistant Semi-Finished Products, Bars, Rods and Sections

Group - Ferrous Stainless Steel Alloys

Sub Group - BS ISO 16143-2 X2CrNiMoCuN25-6-3 (4507-325-20-I) Corrosion-Resistant Semi-Finished Products, Bars, Rods and Sections

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars and Rods

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	0.700 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	24.000 - 26.000
Molybdenum	Mo %	2.500 - 4.000
Nickel	Ni %	5.000 - 7.500
Nitrogen	N %	0.150 - 0.300
Copper	Cu %	1.000 - 2.500
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	700 min.
Proof Strength in Mpa	500 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in HB	270 max.
Impact in Joule	100 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
10250-4 1.4507	EN	European Union	Steel and Forging
10028-7 1.4507	EN	European Union	Steel
10088-3 1.4507	EN	European Union	Steel
10272 1.4507	EN	European Union	Steel and Bars
EN 10088-2 1.4507	DIN	Germany	Steel
EN 10028-7 1.4507	DIN	Germany	Steel
EN 10088-3 1.4507	DIN	Germany	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.