



Material - DIN 1.4462

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN 1.4462 Seemless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Bar and Rods

Chemical Composition			Heat Treatment	
Carbon	С %	0.030 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.	Solution Annealing	
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	21.000 - 23.000		
Molybdenum	Mo %	2.500 - 3.500		
Nickel	Ni %	4.500 - 6.500		_
Nitrogen	N %	0.100 - 0.220	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	640 - 2730
-	-	-	Yield Strength in Mpa	445 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	50 min.
-	-	-	Hardness in HB	290 max.
-	-	-	Impac <mark>t in Joule</mark>	60 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
10216-5 EN 1.4462	BS	British	Tube	
1.4462	EN	European Union	Steel,Bar and Rod	
X2CrNiMoN22-5-3	AFNOR NF	France	Steel	
X2CrNiMoN22-5-3	DIN	Germany	Steel, Bar and Rod	
318 S 13	BS	British	Steel and Plate	
SUS 329J 3L	JIS	Japan Steel, Sheet, Plate and Strip		
X2CrNiMoN22-5-3	UNI	Italy Steel, Sheet, Plate and Strip		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.