



Material - DIN 1.4469

Standard Specification for Corrosion Resistant Steel Casting

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN 1.4469 Corrosion Resistant Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.	Solution Annealing	
Phosphorus	Р%	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	6.000 - 8.000		
Molybdenum	Mo %	4.000 - 5.000		_
Nitrogen	N %	0.120 - 0.250	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	650 - 850.
-	-	-	Yield Strength in Mpa	480 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	50 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1.4469	EN	European Union	0	
GX2CrNiMoN26-7-4	DIN	Germany	Casting	
GX2CrNiMoN25-7-4	DIN	Germany	Casting	
J93404	UNS	USA	Casting	
GX2CrNiMoN26-7-4	AFNOR NF	France	Casting	
A995 5A	ASTM	USA	Casting	
A890 5A	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.