



## Material - DIN 1.4536

### Standard Specification for Corrosion Resistant Steel Castings

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN 1.4536 Corrosion Resistant Steel Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	19.000 - 21.000		
Nickel	Ni %	24.000 - 26.000		
Molybdenum	Mo %	2.500 - 3.500		
Copper	Cu %	1.500 - 2.000		
Nitrogen	N %	0.100 - 0.200		
Iron	Fe %	Balance	<b>Mechanical Properties</b> Tensile Strength in Mpa      440 - 640 Yield Strength in Mpa      200 min. Elongation in %      20 min. Reduction of Area in %      - Hardness in BHN      - Impact in Joule      60 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G X 2 NiCrMoCuN 25-20	DIN	Germany	Casting
T 6 CuMoNiCr 200	STAS	Romania	Casting
J94650	UNS	USA	Casting
A743 CN7MS	ASTM	USA	Casting
A744 CN7MS	ASTM	USA	Casting
A743 J94650	ASTM	USA	Casting
CN-7MS	NBR	Brazil	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.