



Material - DIN 1.4981

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN 1.4981 Seemless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	С %	0.040 - 0.100		
Silicon	Si %	0.300 - 0.600		
Manganese	Mn %	1.500 max.	Solution Annealing	
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	15.500 - 17.500		
Molybdenum	Mo %	1.600 - 2.000		
Nickel	Ni %	15.500 - 17.500		_
Niobium	Nb %	1.200 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	529.6 - 690
-	-	-	Yield Strength in Mpa	215 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	60 J @ RT

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
10216-5 EN 1.4981	BS	British	Tube	
1.4981	EN	European Union	Steel and Tube	
X8CrNiMoNb16 16	EN	European Union	Steel and Tube	
X8CrNiMoNb16 16	DIN	Germany	Steel and Tube	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.