



## Material - DIN 1.4982

### Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN 1.4982 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.150	Solution Annealing	
Silicon	Si %	0.200 - 1.000		
Manganese	Mn %	5.500 - 7.000		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	14.000 - 16.000		
Molybdenum	Mo %	0.800 - 1.200		
Nickel	Ni %	9.000 - 11.000		
Niobium	Nb %	0.750 - 1.250		
Vanadium	V %	0.150 - 0.400		
Boron	B %	0.003 - 0.009	<b>Mechanical Properties</b> Tensile Strength in Mpa      540 - 850 Yield Strength in Mpa      220 min. Elongation in %      25 min. Reduction of Area in %      - Hardness in BHN      - Impact in Joule      50 J @ RT	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4982	BS	British	Tube
1.4982	EN	European Union	Steel
X10CrNiMoMnNbVB15101	EN	European Union	Steel and Tube
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.