



Material - DIN 1.6781

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - DIN 1.6781 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.190	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.550 - 0.800		
Phosphorus	P %	0.015 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	1.300 - 1.800		
Molybdenum	Mo %	0.450 - 0.600		
Nickel	Ni %	3.000 - 3.500		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 750 - 900 Yield Strength in Mpa 600 min. Elongation in % 15 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.6781	EN	European Union	Casting
G17NiCrMo13-6	EN	European Union	Casting
G17NiCrMo13-6	DIN	Germany	Casting
G17NiCrMo13-6	AFNOR NF	France	Casting
G17NiCrMo13-6	UNI	Italy	Casting
GS-18NiCrMo12 6	DIN	Germany	Casting
1.6781	DIN	Germany	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.