



Material - DIN 1.7379

Standard Specification for Steel castings for pressure purposes; Steel grades for use at room temperature and elevated temperatures

Group - Ferrous Mild Steel Alloys

Sub Group - DIN 1.7379 Steel castings for pressure purposes; Steel grades for use at room temperature and elevated temperatures

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.130 - 0.200	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.900		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	2.000 - 2.500		
Molybdenum	Mo %	0.900 - 1.200		
Chromium	Cr %	2.000 - 2.500	Mechanical Properties	
Copper	Cu %	0.300 max.	Tensile Strength in Mpa	590 - 900
Vanadium	V %	0.050 max.	Yield Strength in Mpa	400 min.
Nickel	Ni %	0.400 max.	Elongation in %	15 min.
Iron	Fe %	Balance	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	40 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J22090	UNS	USA	Casting
1.7383	EN	European Union	Forging
10 CD 9.10	AFNOR NF	France	Forging
622	BS	British	Bar
GS 18 CrMo 9 10	ONORM	Australia	Steel
8 CrMoNiNb 9-10	DIN	Germany	Steel
A757 D1N1 D1Q1	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.