



Material - DIN 1.7720

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - DIN 1.7720 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 - 0.150	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.450 max.		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.300 - 0.500		
Molybdenum	Mo %	0.400 - 0.600		
Vanadium	V %	0.220 - 0.300		
Tin	Sn %	0.025 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	510 - 660
-	-	-	Yield Strength in Mpa	295 min.
-	-	-	Elongation in %	17 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	27 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.7720	EN	European Union	Casting
1.772	EN	European Union	Casting
660	BS	British	Steel and Plates
G 12 MoCrV 5 2	EN	European Union	Casting
G 12 MoCrV 5-2	DIN	Germany	Casting
G12MoCrV5-2	AFNOR NF	France	Casting
G12MoCrV5-2	UNI	Italy	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.