



## Material - DIN 11 CrMo 9-10

### Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - DIN 11 CrMo 9-10 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Flat

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 - 0.150	Quenching + Tempering	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.400 - 0.800		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	2.000 - 2.500		
Molybdenum	Mo %	0.900 - 1.100		
Copper	Cu %	0.250 max.		
Nitrogen	N %	0.012 max.		
Iron	Fe %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      450 - 680 Yield Strength in Mpa      265 min. Elongation in %      17 min. Reduction of Area in %      - Hardness in BHN      - Impact in Joule      27 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-2	BS	British	Steel and Flat
1.7383	DIN	Germany	Steel and Flat
1.7383	DIN	Germany	Steel and Flat
11CrMo9-10	AFNOR NF	France	Steel and Flat
11CrMo9-10	BS	British	Steel and Flat
11CrMo9-10	ISO	International	Steel and Tube
11CrMo9-10	UNI	Italy	Steel and Flat

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.