GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - DIN 17458 1.4306 (X 2 CrNi 19 11)

Standard Specification for Seamless Circular Austenitic Stainless Steel Tubes Subject to Special Requirements

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN 17458 1.4306 (X 2 CrNi 19 11) Seamless Circular Austenitic Stainless Steel Tubes Subject to Special Requirements

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel and Tubing

Chemical Composition		
Carbon	C %	0.030 max.
Chromium	Cr %	18.000 - 20.000
Nickel	Ni %	10.000 - 12.500
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	460 - 680
Proof Strength in Mpa	215 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in HBW	-
Impact in Joule	85 @ RT

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J 405 304L	SAE	USA	Steel
EN 10088-2 X 2 CrNi 19-11	UNI	Italy	Steel and Casting
EN 10088-1 X2CrNi19-11	AFNOR NF	France	Steel
EN 10088-3 X2CrNi19-11	AFNOR NF	France	Steel
10088-3 X 2 CrNi 19 11	EN	European Union	Steel
1654-5 X 2 CrNi 19 11	DIN	Germany	Steel
1654-5 1.4306	DIN	Germany	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.