



Material - DIN 20 CrMoV 13 5

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - DIN 20 CrMoV 13 5 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.170 - 0.230	Quenching + Tempering	
Silicon	Si %	0.150 - 0.350		
Manganese	Mn %	0.300 - 0.500		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	3.000 - 3.300		
Molybdenum	Mo %	0.500 - 0.600		
Vanadium	V %	0.450 - 0.550		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 740 - 880 Yield Strength in Mpa 590 min. Elongation in % 17 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 55 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.7779	EN	European Union	Steel and Tube
1.7779	DIN	Germany	Steel and Tube
1.7779	DIN	Germany	Steel and Tube
20 CrMoV 13 5	MSZ	Hungary	Steel
15423	CSN	Czech Republic	Steel
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +91846916029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.