



## Material - DIN 8 CrMoNiNb 9-10

### Standard Specification for Low alloyed CrMoNiMn steel

Group - Ferrous Mild Steel Alloys

Sub Group - DIN 8 CrMoNiNb 9-10 Low alloyed CrMoNiMn steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.150 - 0.500		
Manganese	Mn %	0.400 - 0.800		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	2.000 - 2.500		
Molybdenum	Mo %	0.900 - 1.100		
Nickel	Ni %	0.300 - 0.800		
Aluminium	Al %	0.050 max.		
Iron	Fe %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      390 - 610 Yield Strength in Mpa      215 min. Elongation in %      17 min. Reduction of Area in %      38 min. Hardness in BHN      - Impact in Joule      27 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J22090	UNS	USA	Casting
1.7379	DIN	Germany	Forging
1.7383	EN	European Union	Forging
10 CD 9.10	AFNOR NF	France	Forging
622.0000	BS	British	Bar
GS 18 CrMo 9 10	ONORM	Australia	Steel
A757 D1N1 D1Q1	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.