



Material - DIN G X 22 CrNi 17

Standard Specification for Corrosion Resistant Steel Castings

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN G X 22 CrNi 17 Corrosion Resistant Steel Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.270	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Nickel	Ni %	1.000 - 2.000		
Iron	Fe %	Balance		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	780 - 980
			Yield Strength in Mpa	590 min.
			Elongation in %	4 min.
			Reduction of Area in %	-
			Hardness in BHN	200 - 300
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J91803	UNS	USA	Casting
AoX 20 CrNi 17-2	MSZ	Hungary	Casting
ANC 2	BS	British	Casting
Z 20 Cn 17.2M	AFNOR NF	France	Casting
1.4059	DIN	Germany	Casting
A743 CB30	ASTM	USA	Casting
3444 Grade 12	IS	India	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.