



Material - DIN GS-23Mn6

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - DIN GS-23Mn6 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.250		
Silicon	Si %	0.300 - 0.500		
Manganese	Mn %	1.500 - 1.700		
Phosphorus	Р%	0.015 max.	Normalising or Annealing or Hardening + Tempering	ardening + Tempering
Sulphur	S %	0.003 max.		
Chromium	Cr %	0.300 max.		
Iron	Fe %	Balance		
-	-			
-	-	-	Mechanical Pro	operties
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Gr <mark>ade Belong</mark> to the Industry		
1.1118	DIN	Germany	Casting		
1.1119	EN	European Union	Casting		
1.1119	DIN	Germany	Casting		
GS-24Mn6	DIN	Germany	Casting		
1.1118	EN	European Union	Casting		
G23 Mn6	EN	European Union	Casting		
GS-24Mn6	EN	European Union	Casting		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS