



Material - DIN GX130CrSi29

Standard Specification for Heat Resistant Alloy Steel Castings

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN GX130CrSi29 Alloy Steel Casting for Heat Resistant

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	1.200 - 1.400	AS-Cast or Annealing	
Silicon	Si %	1.000 - 2.500		
Manganese	Mn %	0.500 - 1.000		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	27.000 - 30.000		
Cobalt	Co %	0.500 max.		
Copper	Cu %	0.200 max.		
Niobium	Nb %	0.200 max.		
Nickel	Ni %	1.000 max.		
Vanadium	V %	0.080 max.	Mechanical Properties	
Tungsten	W %	0.200 max.	Tensile Strength in Mpa	-
Iron	Fe %	Balance	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
			Hardness in BHN	250 - 350
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4777	DIN	Germany	Casting
4522 Grade 3	IS	India	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.