



## Material - DIN X 8 CrNiMoVNb 16 13

## **Standard Specification for Seemless Steel Tubes for Pressure Purposes**

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - DIN X 8 CrNiMoVNb 16 13 Seemless Steel Tubes for Pressure Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.100	Solution Annealing	
Silicon	Si %	0.300 - 0.600		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	15.500 - 17.500		
Molybdenum	Mo %	1.100 - 1.500		
Nickel	Ni %	12.500 - 14.500		-
Vanadium	V %	0.600 - 0.850	Mechanical Properties	
Niobium	Nb %	1.200 max.	Tensile Strength in Mpa	540 - 740
Nitrogen	N %	0.060 - 0.140	Yield Strength in Mpa	255 min.
Iron	Fe %	Balance	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	40 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
10216-5 EN 1.4988	BS	British	Tube	
1.4988	DIN	Germany	Steel	
1.4988	EN	European Union	Steel	
X8CrNiMoVNb16-13	EN	European Union	Steel and Flat	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.