



Material - DIN X1NiCrMoCu31-27-4

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN X1NiCrMoCu31-27-4 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Bar and Rods

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	Solution Annealing	
Silicon	Si %	0.700 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	26.000 - 28.000		
Molybdenum	Mo %	3.000 - 4.000		
Nickel	Ni %	30.000 - 32.000		
Copper	Cu %	0.800 - 1.500		
Nitrogen	N %	0.110 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 500 - 2100 Yield Strength in Mpa 215 min. Elongation in % 20 min. Reduction of Area in % - Hardness in HB 230 max. Impact in Joule 60 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4563	BS	British	Tube
1.4563	DIN	Germany	Steel, Plate and Strip
1.4563	EN	European Union	Steel, Plate and Strip
X1NiCrMoCu31-27-4	UNI	Italy	Steel, Plate and Strip
X1NiCrMoCu31-27-4	AFNOR NF	France	Steel
X1NiCrMoCu31 27 4	ISO	International	Steel, Bar and Rod
Z2NCDU31-27	AFNOR NF	France	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.