



Material - DIN X20CrMoV 121

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - DIN X20CrMoV 121 Seemless Steel Tubes for Pressure Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging, Rolling, Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.170 - 0.230		
Silicon	Si %	0.400 max.		
Manganese	Mn %	1.000 max.	Normalising + Tempering	
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	10.000 - 12.500		
Molybdenum	Mo %	0.800 - 1.200		
Nickel	Ni %	0.300 - 0.800		-
Vanadium	V %	0.250 - 0.350	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	700 - 850
-	-	-	Yield Strength in Mpa	500 min.
-	-	-	Elongation in %	16 min.
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	14 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1.4922	EN	European Union	Forging, Rolling, Steel and Bar	
1.4922	DIN	Germany	Forging, Rolling, Steel and Bar	
1.4922	DIN	Germany	Forging, Rolling, Steel and Bar	
X20CrMoV121	ISO	International	Forging, Rolling, Steel and Bar	
12Cr10MoVNi70.47	MSZ	Hungary	Steel and Tube	
762	BS	British	Steel and Tube	
X20CrMoNiV11 11	ISO	International	Steel and Tube	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.