



Material - EN 1.0213

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - EN 1.0213 Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 - 0.100	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.100 max.		
Manganese	Mn %	0.200 - 0.450		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.025 max.		
Aluminium	Al %	0.020 - 0.060		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 490 min. Yield Strength in Mpa - Elongation in % - Reduction of Area in % 63 max. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G17CrMo5-5	BS	British	Plate, Tubes and Forging
QSt 34-3	DIN	Germany	Plate, Tubes and Forging
C8C	ISO	International	Casting
1.0213	AFNOR NF	France	Casting
1.0213	DIN	Germany	Casting
1.0213	MSZ	Hungary	Casting
1.0213	UNI	Italy	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.