

Material - EN 1.4008

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - EN 1.4008 Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.		
Silicon	Si %	1.000 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.000 max.		lizing or Hardoning and
Phosphorus	Р%	0.035 max.		с С
Sulphur	S %	0.025 max.		iig
Chromium	Cr %	12.000 - 13.500		
Nickel	Ni %	1.000 - 2.000		
Molybdenum	Mo %	0.200 - 0.500		
Copper	Cu %	0.300 max.	Mechanical Properties	
Vanadium	V %	0.080 max.	Tensile Strength in Mpa	590 min.
Iron	Fe %	Balance	Yield Strength in Mpa	440 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in BH</mark> N	-
-	-	-	Impac <mark>t in Joule</mark>	27 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
410C21	BS	British	Casting	
1.4008	ONORM	Australia	Casting	
1.4011	ONORM	Australia	Casting	
GX12Cr12	ONORM	Australia	Casting	
GX7CrNiMo12-1	ONORM	Australia	Casting	
1.4011	EN	European Union	Casting	
GX12Cr12	EN	European Union	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS