



## Material - EN 1.4307

**Standard Specification for Iron-Chromium-Nickel, Rod, Bar, Wire and Forging**

**Group - Ferrous Stainless Steel Alloys**

**Sub Group - EN 1.4307 Iron-Chromium-Nickel, Rod, Bar, Wire and Forging**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Rod, Bar, Wire and Forging**

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	17.500 - 19.500		
Nickel	Ni %	8.000 - 10.000		
Nitrogen	N %	0.110 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 - 2100
-	-	-	Yield Strength in Mpa	175 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	63 min.
-	-	-	Hardness in HB	215 max.
-	-	-	Impact in Joule	60 @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
304 S11	BS	British	Bright Bars, Hot Rolled and Cold Rolled, Coil
SUS 304L	JIS	Japan	Hot Rolled Equal Leg Angles
04CH 18N10	GOST	Russia	Pipes, Fittings, Bar, Sheet and Forging
304L	AISI	USA	Bar, Wire, Strip, Plat, Sheet and Forging
1.4306	DIN	Germany	Cold Rolled, Strips, Slit, Coils and Forging
A743 CF3	ASTM	USA	Casting
A351 CF3	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.