



Material - EN 1.4547

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - EN 1.4547 Seemless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Bar and Rods

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.		
Silicon	Si %	0.700 max.		
Manganese	Mn %	1.000 max.	Solution Annealing	
Phosphorus	Р%	0.030 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	19.500 - 20.500		
Molybdenum	Mo %	6.000 - 7.000		
Nickel	Ni %	17.500 - 18.500		_
Copper	Cu %	0.500 - 1.000	Mechanical Properties	
Nitrogen	N %	0.180 - 0.250	Tensile Strength in Mpa	500 - 2100
Iron	Fe %	Balance	Yield Strength in Mpa	300 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	260 max.
-	-	-	Impac <mark>t in Joule</mark>	60 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
0216-5 EN 1.4547	BS	British	Tube	
1.4547	DIN	Germany	Steel, Bar and Rod	
X1CrNiMoCuN20-18-7	AFNOR NF	France	Steel, Bar and Rod	
X1CrNiMoCuN20-18-7	UNI	Italy	Steel, Sheet, Strip and Plate	
X1CrNiMoCuN20-18-7	DIN	Germany	Steel, Sheet, Strip and Plate	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.